

Stucco



1-Product description

1.1 USE

- This stucco is principally used as an exterior wall and foundation coating.
- Available in grey or white, it can be applied on any cement-based surface or on a wire mesh.
- For interior or exterior use.
- This stucco can be colored with our Easy-match coloring system to obtain a wide variety of pastel colors.

2- Installation

2.1 SURFACE PREPARATION

- Surface to be covered must be sound, clean and free from bond inhibiting materials such as dust, oil or paint.
- Thoroughly wet the surface to be covered 12 to 24 hours before the application..
- Humidify the surface (avoid accumulation) before the application.
- Make sure the temperature is between 5 °C (40 °F) and 35 °C (95 °F), during the application and for the following 72 hours.

2.2 RECOMMENDATIONS

- It is possible to use our All-crete concrete adhesive as a primer coat to increase adhesion between the old surface and the stucco.

2.3 MIXING

- Pour 4.0 to 4.5 litres (0.9 to 1.0 gallon) of water per 22.7 kg (50 lb) bag into a clean container.
- Gradually add the dry ingredients while mixing with a drill equipped with a mixing attachment such as a paint mixer.
- Mix for a period of 3 minutes scraping the sides of the container until a homogeneous consistency is obtained.
- If the mixture is too thick, gradually add water avoiding excess.

2.4 APPLICATION

- This stucco is applied in two coats.
- Apply the first coat with a trowel spreading on a thin and well-packed coat. It is recommended to make the surface rough with a notched trowel to increase the adhesion with the second coat.
- Wait 24 hours before you apply the second coat.
- To apply the second coat, dampen the surface then apply the stucco with a brush, a sponge or a finishing trowel according to the desired finish.
- Working time is approximately 2 hours; do not add water to recover workability.
- The thickness of the 2 coats (combined) should have a minimum of 19 mm (3/4 in).

2.5 PROTECTION AND CURING

- Once stucco is dry, it is **IMPORTANT** to frequently humidify the surface with a light spray during the next 3 days.

2.6 CLEANING

- Clean tools with water while mixture is not yet hardened. Once it is hard, only a mechanical cleaning will be efficient.

3. Yield

- A 22.7 kg (50 lb) bag will cover approximately 3.7 m² (40 ft²) at a thickness of 3 mm (1/8 in).

4. Packaging

- This product is available in 22.7 kg (50 lb) bag.

5. Storage

- Store in a cool, dry place. Avoid placing the bag directly on the floor.
- Shelf life is one year in unopened bags.
- Discard product that has been damaged by water or humidity or that contains hard lumps.

6. First aid

This product contains portland cement and may cause eye, skin and respiratory system irritation. Wear rubber gloves, safety glasses and approved dust mask. If swallowed, call a Poison Control centre or doctor immediately. Do not induce vomiting.

Technical data sheet

#12.11 (white), #12.15 (grey) , Stucco, 0804, page #2

In case of contact with eyes, rinse well with water for 15 minutes. In case of skin contact, rinse well with water. Keep out of reach of children. Consult the safety data sheet for more information.

7. Technical services

Contact Daubois for more information about application methods or conditions or to obtain the latest version of our technical documents.

Phone: 1-800-561-2664
(514) 328-1253

Fax: (514) 328-7694

Daubois inc
6155, boul. des Grandes Prairies
Saint-Léonard, Qc H1P 1A5
Canada
<http://www.daubois.com>

8. Warranty

Daubois guarantees that this product will perform as specified in this technical data sheet and suits the application for which it was intended. Nonetheless, Daubois does not offer any explicit or implicit warranty. Under this warranty, Daubois' responsibility is limited to either replace or refund the cost of the product proved defective.